

INCATI






Innovative Carpet Tiles

QUARTZ

version 4/09/2019
replaces 10/07/2019

Manufacturing type	Herstellingsart	Mode fabrication	Productie methode			tufted 1/10"
Construction	Structuur	Structure	Structuur			loop pile
Pile composition	Polmaterial	Couche d'usure	Poolsamenstelling			100% PA 6 BCF
Dye method	Farbgestaltung	Coloration	Kleurverwerking			piece dyed
Primary backing	Trägermaterial	Premier dossier	Tuftdoek			polyester fleece
Secondary backing	Rückenausrüstung	Dossier	Rug			bitumen with glass fibre scrim
Pile weight	Poleinsatzgewicht	Poids de velour	Poolgewicht	ISO 2424	g/m2	550 (+/-)
Total weight	Gesamtgewicht	Poids total	Totaal gewicht	ISO 8543	g/m2	4.300 (+/-)
Pile height	Polhöhe	Hauteur du velours	Poolhoogte	ISO 1766	mm	3,0 (+/-)
Total height	Gesamtdicke	Epaisseur totale	Totale dikte	ISO 1765	mm	6,0 (+/-)
Tuft density	Noppenzahl	Nombre de touffes	Aantal punten	ISO 1763	/m2	164.000 (+/-)
Size	Abmessung	Dimension	Afmeting		cm	50 x 50
Packing	Verpackung	Emballage	Verpakking			20 per box 5 m2
Classification	Klassifikation	Classement	Gebriuksklasse	EN 1307		33 heavy commercial
Comfort rating	Komfortklasse	Classement confort	Comfort klasse	EN 1307		LC 1
Castor chair	Stuhlrolleneignung	Chaise à roulettes	Rolstoelgeschikt	EN 985		A intensive
Dimensional stability	Dimensionstabilität	Stabilité dimensionnelle	Dimensionele stabiliteit	EN 986		≤ 0,2%
Fire resistance	Brennverhalten	Comportement feu	Brandgedrag	EN 13501-1		Bfl-S1 loose laid
Permanent antistatic	Permanent Antistatisch	Antistatique permanent	Permanent antistatisch	ISO 6356	kV	≤ 2,0
Transversal resistance	Durchgangswiderstand	Résistance transversale	Doorgangsweerstand	ISO 10965	Ω	≤ 10¹⁰
Thermal resistance	Wärmedurchlaßwiderstand	Résistance thermique	Warmtedoorlaatweerstand	ISO 8302	m2/K/W	0,057
Sound absorption	Schallabsorptionsgrad	Absorption phonique	Geluidsabsorptie	ISO 354	α _w	0,15
Impact sound reduction	Trittschallverbesserungsmaß	Isolation phonique	Geluidsisolatie	ISO 10140	ΔL _w	25 dB
				ISO 10140	ΔL	39 dB (1000 Hz)
Colour fastness light	Lichtechtheit	Solidité à la lumière	Lichtechtheid	ISO 105 B02		≥ 7
Rubbing fastness	Reibechtheit	Solidité au frottement	Wrijftechtheid	ISO 105 X12		≥ 4-5
				DIBt Nr.		Z-156.601-1467



 19 EN 14041 DOP 000423T-001	 Bfl-s1
	 DS
TAPIBEL NV Industrielaan 4 B-3900 Pelt Belgium +32 11 80 48 50 sales@incati.be www.incati.be	 DL PCP
	 NA HCHO
EN 1307 for use as floorcovering in buildings (EN 14041) according to the manufacturer's specification	



TÜV Emission testing

Results comply with emission threshold of


- AgBB - Germany
- Belgian VOC regulation
- BREEAM Exemplary level
- French VOC regulation
- LEED V4 (outside North America)



INSTALLATION



ALSO AVAILABLE



special colours : minimum 400m2

MAINTENANCE

visit our website www.incati.be/en/faq-carpet-tiles
for more detailed information

These technical details are approximate. Complete specification details and associated certificates together with tolerances applying to the above can be provided upon request, if available. We reserve the right to alter specifications without notice. Due to the method of manufacture, perfect pattern/colour matching cannot be guaranteed. Shading/pile reversal might occur in cut pile carpets, without affecting overall quality and suitability. It is not considered as a manufacturing fault.