

INCATI

Innovative Carpet Tiles

VOGUE

version 22/04/2020
replaces

Manufacturing type	Herstellungsverfahren	Mode fabrication	Productie methode			
Construction	Struktur	Structure	Structuur	tufted 1/10"		
Pile composition	Polmaterial	Couche d'usure	Poolsamenstelling	loop pile		
Dye method	Farbgestaltung	Coloration	Kleurverwerking	100% PA 6 BCF		
Primary backing	Trägermaterial	Premier dossier	Tuftdoek	solution dyed		
Secondary backing	Rückenausrüstung	Dossier	Rug	polyester fleece		
Pile weight	Poleinsatzgewicht	Poids de velour	Poolgewicht	ISO 2424	g/m2	550 (+/-)
Total weight	Gesamtgewicht	Poids total	Totaal gewicht	ISO 8543	g/m2	4.300 (+/-)
Pile height	Polhöhe	Hauteur du velours	Poolhoogte	ISO 1766	mm	3,0 (+/-)
Total height	Gesamtdicke	Epaisseur totale	Totale dikte	ISO 1765	mm	6,0 (+/-)
Tuft density	Noppenzahl	Nombre de touffes	Aantal punten	ISO 1763	/m2	164.000 (+/-)
Size	Abmessung	Dimension	Afmeting	cm 50 x 50		
Packing	Verpackung	Emballage	Verpakking	20 per box 5 m2		
Classification	Klassifikation	Classement	Gebriuksklasse	EN 1307	33	heavy commercial
Comfort rating	Komfortklasse	Classement confort	Comfort klasse	EN 1307	LC 1	
Castor chair	Stuhllöseignung	Chaise à roulettes	Roelstoelgeschikt	EN 985	A	intensive
Dimensional stability	Dimensionstabilität	Stabilité dimensionnelle	Dimensionele stabiliteit	EN 986	≤ 0,2%	
Fire resistance	Brennverhalten	Comportement feu	Brandgedrag	EN 13501-1	Bfl-S1	loose laid
Permanent antistatic	Permanent Antistatisch	Antistatique permanent	Permanent antistatisch	ISO 6356	kV	≤ 2,0
Transversal resistance	Durchgangswiderstand	Résistance transversale	Doorgangsweerstand	ISO 10965	Ω	≤ 10⁹
Thermal resistance	Wärmedurchlaßwiderstand	Résistance thermique	Warmteoorlaafweerstand	ISO 8302	m2/K/W	0,066
Sound absorption	Schallabsorptionsgrad	Absorption phonique	Geluidsabsorptie	ISO 354	α _w	0,15
Impact sound reduction	Trittschallverbesserungsmaß	Isolation phonique	Geluidsisolatie	ISO 10140	ΔL _w	25 dB
				ISO 10140	ΔL	39 dB (1000 Hz)
Colour fastness light	Lichtechtheit	Solidité à la lumière	Lichtechtheid	ISO 105 B02	≥ 6	
Rubbing fastness	Reibechtheit	Solidité au frottement	Wrijftechtheid	ISO 105 X12	≥ 4-5	
				DIBt Nr.	Z-156.601-1467	



SDN
solution dyed nylon
Stoepvloer met draad

 20 EN 14041 DOP 000423T-001	 Bfl-S1
	 DS
TAPIBEL NV Industrielaan 4 B-3900 Pelt Belgium +32 11 80 48 50 sales@incati.be www.incati.be	 DL
	 PCP
 NA	
 HCHO	
EN 1307 for use as floorcovering in buildings (EN 14041) according to the manufacturer's specification	



TÜV Emission testing

Results comply with emission threshold of


- AgBB - Germany
- Belgian VOC regulation
- BREEAM Exemplary level
- French VOC regulation
- LEED V4 (outside North America)



INSTALLATION



ALSO AVAILABLE



MAINTENANCE

visit our website www.incati.be/en/faq-carpet-tiles
for more detailed information

These technical details are approximate. Complete specification details and associated certificates together with tolerances applying to the above can be provided upon request, if available. We reserve the right to alter specifications without notice. Due to the method of manufacture, perfect pattern/colour matching cannot be guaranteed.

Shading/pile reversal might occur in cut pile carpets, without affecting overall quality and suitability. It is not considered as a manufacturing fault.